High Performance 2D Schottky Diodes Utilizing Chemical Vapour Deposition Grown Graphene-MoS₂ Heterojunctions

*Hefu Huang¹, Wenshuo Xu¹, Tongxin Chen¹, Ren-Jie Chang¹, Yuewen Sheng¹, Qianyang Zhang¹,
Linlin Hou¹, Jamie H. Warner^{1*}*

¹Department of Materials, University of Oxford, Parks Road, Oxford, OX1 3PH, United
Kingdom

[*Jamie.warner@materials.ox.ac.uk](mailto:Jamie.warner@materials.ox.ac.uk);

Abstract

Heterostructures based on two-dimensional materials have attracted enormous interest as they display unique functionalities and have potential to be applied in next-generation electronics. In this report, we fabricated 3 types of heterostructures based on CVD-grown graphene and MoS₂. A significant rectification was observed in Au-MoS₂-Gr heterojunction, with a rectification ratio over 2×10^4 . The rectifying behavior is reproducible among all 44 testable devices and is attributed to asymmetrical Schottky barrier at Au-MoS₂ and MoS₂-graphene contacts. This rectification can be tuned by external gating and laser illumination, which have different impact on the rectifying ratio. This modulation of Schottky barrier is evidenced by output characteristics of two symmetrical heterostructures: Au-MoS₂-Au and Gr-MoS₂-Gr field-effect transistors. The effective heights of MoS₂-graphene, and MoS₂-Au Schottky barrier and their response to back-gate voltage and laser irradiation, were extracted from output characteristics of Au-MoS₂-Au and Gr-MoS₂-Gr field-

effect transistors. The tuned Schottky barriers could be explained by Fermi level change of graphene and MoS₂. These results contributed to our understanding of 2D heterostructures and have potential applications in novel electronics and optoelectronics.

KEYWORDS: graphene, molybdenum disulfide, heterostructure, rectification, Schottky barrier

Introduction

Two-dimensional (2D) materials are seen as promising candidates for next-generation electronics and optoelectronics as they show unique properties. To date, many 2D materials have been studied. For example, graphene is a semi-metal with high mechanical strength, thermal conductivity and transparency.¹ Transition metal dichalcogenide (TMD) monolayers, such as MoS₂, WS₂, MoSe₂ and WSe₂ are ultrathin semiconductors with a direct band gap.²⁻⁹ Hexagonal boron nitride (h-BN) is an insulator of good heat and chemical resistance.¹⁰ By combining these 2D crystals, van der Waals heterostructures can be created. Novel 2D devices, such as transistors, logic devices, light emitting diodes and photodetectors have been fabricated using 2D heterostructures.¹¹⁻¹⁸ Among these heterostructures, graphene-TMDs heterostructures are particularly interesting since many exciting phenomena have been observed.¹⁹⁻³⁰ For example, Gr-WS₂ heterostructures exhibit gate-tunable rectification with a maximum rectification ratio of 10^3 .¹⁹ In graphene-MoS₂ hybrids, a responsivity of 5×10^8 A/W at room temperature was observed.²³ Current modulation exceeding 1×10^6 can be achieved in Gr-MoS₂-Gr vertical tunneling transistor.²⁵ Similar to conventional metal-semiconductor heterostructure,³¹ Schottky barriers can be formed between metal-TMDs and graphene-TMDs interfaces, which is supported by the observation of non-linearity output characteristics of TMDs transistors with Au and graphene electrodes.^{30,32} The interfaces are found

to be sensitive to external environments, resulting in tunable properties of the heterostructures. However, most 2D Gr-TMDs Heterostructures previously studied are based on mechanical exfoliated 2D materials thus the fabrication yield and scalability are severely restrained. Due to the small number of tested devices, it is challenging to obtain results that are statistically robust. Also, to fully understand the properties of the heterostructures, the responses of Au-TMDs and TMD-graphene interfaces to external modulations need to be thoroughly studied.

Here, we studied Au-MoS₂-Gr heterojunctions made from all CVD-grown 2D materials. A strong current rectification was observed in nearly all 44 devices tested, with a maximum rectification ratio over 2×10^4 . Both external gating and laser illumination (532nm) can tune the rectifying behavior, which implies modified Schottky barriers of Au-MoS₂ and MoS₂-Gr interface. It was also observed that laser irradiation could switch on the off-current thus greatly reduce the rectification ratio, while the rectification ratio under gating is relatively stable. To explain the different tunabilities between laser and gating, we fabricated MoS₂ field effect transistors with Au and Gr electrodes separately. Au-MoS₂ and MoS₂-Gr Schottky barriers heights and their responses to external gate and laser were extracted from the output characteristics of the two FETs respectively. The height difference of Au-MoS₂ and MoS₂-Gr interface was found to be relatively constant under external gate voltage but quickly narrows down under laser irradiation.

Results and Discussion

Figure1. Fabrication process and SEM image of devices of 3 types of structures. (a) Fabrication process schematic of Au-MoS₂-Au, Au-MoS₂-Gr and Gr-MoS₂-Gr devices designed for this experiment. 2 steps of graphene patterning are used to achieve higher fabrication accuracy. (b) – (d) Configuration schematic and SEM images of fabricated structures: (b) Au-MoS₂-Au. (c) Au-MoS₂-Gr. (d) Gr-MoS₂-Gr. In SEM images,

Cr/Au bond pads are indicated with the golden dashed line, MoS₂ domains with green dashed line and graphene with the blue dashed line.

The fabrication process of all three types of devices, Au-MoS₂-Au, Au-MoS₂-Gr, and Gr-MoS₂-Gr, is shown in **Figure 1a**. It takes up to 4 steps: 1. A clean chip (Si/SiO₂ 300nm) was spin-coated with PMMA and patterned using electron-beam lithography and Cr(10nm)/Au(80nm) was deposited onto the chip using thermal evaporation. 2. Graphene was transferred and roughly defined using negative resist and etched by oxygen plasma. 3. Graphene was finely defined using PMMA and etched by oxygen plasma. The etching of graphene took two steps as higher resolution and accuracy can be achieved by using PMMA. 4. MoS₂ domains were subsequently transferred onto the chip. For Au-MoS₂-Au structure, step 2 and 3 are not necessary as no graphene was used. Both MoS₂ domains and graphene films were synthesized using CVD method and transferred using wet transfer method as previously reported.³³⁻³⁵ Other details were further described in the methodology part.

The feature of the three types of devices is designed to be comparable with each other. On each 1cm×1cm silicon chip, 495 devices (33rows × 15columns) were made. Each device contains two bond pads of 150 um×150 um and source-drain electrodes arm of either Cr/Au or graphene. The width of the source-drain electrodes arms is 20 um and the gap between the two arms is 1um, which is designed to accommodate the conductivity of CVD-synthesized MoS₂ domains. It's worth noting that MoS₂ domains were randomly distributed over the chip and the edge length the domains vary from 10 um to 40 um. Among all 495 devices, about 10% of them have sufficient MoS₂ coverage, giving us about 50 functional devices for Au-MoS₂-Au. As the success rate of graphene

patterning is around 80%, the number of testable devices is about 40 for both Au-MoS₂-Gr and Gr-MoS₂-Gr.

Figure 1b, 1c, and 1d depict the cross-sectional schematic of A-MoS₂-Au, Au-MoS₂-Gr, and Gr-MoS₂-Gr devices respectively. Alongside shows the device array, morphology and detailed feature of the heterostructure. In the SEM images, golden, green and blue dashed lines are used to indicate Cr/Au, MoS₂ domains, and graphene film. Given that in many cases MoS₂ domains cannot fully cover Cr/Au or graphene electrodes, the active region of the devices is calculated using the overlapping area. Due to different contacts between MoS₂ channel and Au or Gr electrodes, the three devices display distinctive characteristics. For convenience, properties of symmetrical structure (Au-MoS₂-Gr), and asymmetrical structures (Au-MoS₂-Au and Gr-MoS₂-Gr) were discussed separately.

Figure 2. Raman and PL characterization of CVD-grown graphene and MoS₂. (a) Optical image of Au-MoS₂-Gr heterostructure showing Cr/Au in golden, MoS₂ in green and graphene in blue. (b) Raman spectra of graphene electrodes. (c) Raman spectra of the MoS₂ domain in the

green framed region in (c) under 532 nm laser. (d). PL spectra of MoS₂ domains: blue for MoS₂ on SiO₂/Si and green for MoS₂ on graphene. The two peaks near 580 nm and 620 nm corresponds to the G peak and 2D peak of graphene underneath. (e) PL spectrum and peaks fitting of MoS₂ on SiO₂/Si (f) PL spectrum and peaks fitting of MoS₂ on graphene.

2D materials used in the structures were characterized using Raman and photoluminescence (PL) spectroscopy. **Figure 2a** shows an optical image of the Au-MoS₂-Gr device including a spike-shaped MoS₂ domain. Optical images of Au-MoS₂-Au and Gr-MoS₂-Gr are included in supporting information. **Figure 2b** shows the Raman spectra of the graphene electrode, under green laser with $\lambda = 532$ nm. The curve shows a 2D/G peak intensity ratio of about 2 (1.95 to be precise, after removing the background), indicating that the graphene used in the device is in general monolayer.³⁶ A weak D peak suggests that the quality of graphene is good and contains only a few defects. Multilayer graphene region can also be found but doesn't influence the property of the devices.

Figure 2c shows the Raman spectra of MoS₂ domains used in the device. Two characteristic Raman vibration modes can be found in the spectra. The E_{2g} mode stands for the in-plane vibration of molybdenum and sulfur atoms. The A_{1g} mode is associated with the out-of-plane vibration of sulfur atoms. We can extract the thickness of MoS₂ domains using the frequency difference between these two modes. The spectra show that the two peaks located at 384.08 cm⁻¹ and 404.64 cm⁻¹, giving a frequency difference Δk of 20.56 cm⁻¹. This result means that this CVD-grown MoS₂ is a monolayer, which is consistent with previous work.^{34, 37}

We also studied the photoluminescence (PL) of monolayer MoS₂ on SiO₂ and graphene substrate, as depicted in **Figure 2d**. All PL spectra in the figure were normalized against the Raman intensity. For the PL spectrum of MoS₂ transferred on graphene substrate, we could observe that PL peak intensity was significantly quenched compared to that on SiO₂ substrate. The quench corresponds to the interlayer coupling and electronic interaction with graphene substrate, as the photo-excited electrons and holes from MoS₂ domain could easily transfer to graphene, resulting in a decreased recombination process of excitons and the quenching of PL signal. This indicates a good contact between graphene and MoS₂ interface, which is in good agreement with previous reports.^{38, 39} The two additional peaks near 580 nm and 620 nm corresponds to the G peak and 2D peak of graphene underneath.

Furthermore, we performed the peak fitting on PL spectra based on Lorentz peak function to study the relative luminescence quantum efficiency. As is shown in **Figure 2e** and **2f**, the PL spectra of MoS₂ have three subpeaks which correspond to A, A⁻ and B peaks respectively. The peak A and B are associated with the direct transition from conduction band to two spin-orbit split valence band at the K point. The peak A⁻, which locates at slightly lower energy than A peak, corresponds to the recombination of negatively charged excitons of trions A⁻. The trion A⁻ arises from a free electron bounded to a neutral exciton via Coulomb interaction since MoS₂ could be easily negatively doped by contamination or contact with the substrate.

Upon comparing the integrated A and A⁻ PL peaks of different spectra, we noticed that the PL intensity ratio of A to A⁻ (A/A⁻) changed. The A/A⁻ ratio presents the relative populations of neutral and charged A excitons. In the PL spectra of MoS₂ transferred on SiO₂, the PL peak is dominated by A⁻ peak, revealing a high degree of charged impurities from SiO₂ substrate which is

in agreement with previous studies.^{30, 39} On the contrary, for MoS₂ transferred on a graphene substrate, the A/A'- ratio was reversed. This is due to the fact that conducting graphene could act as P-doping agent for MoS₂. Moreover, a slight red shift of A peak could be observed alongside with the change of A/A'- ratio. Previous studies suggested that the uniaxial tensile strain in MoS₂ domains could result in the peak shift of A peaks. We speculate that the redshift is associated with the difference in uniaxial tensile strain in MoS₂ domain introduced by SiO₂ and graphene substrate respectively.

Figure 3. Characteristics of the MoS₂-Gr diode. (a) Typical output characteristics of the diode. Inset: schematic figure and circuit analogy of the device. (b) Statistics of rectification of 44 working devices. The sign of the current is ignored when a negative bias is applied, to better illustrate the On-Off states. (c) Gate-voltage dependence of the rectifying behavior. (d) Laser-power dependence of the rectifying behavior. (e) Rectification ratio, defined as $R = I_{ds}(V_{ds} = 2V) / I_{ds}(V_{ds} = -2V)$, under various gate voltages. (f) Rectification ratio under various laser power.

To understand the property of MoS₂-Gr heterostructure, we conducted I-V measurements under different gate voltages and illumination intensities. All electronic and optoelectronic measurements reported here were done at room temperature. The results of Au-MoS₂-Gr devices are shown in **Figure 3** and the results of Au-MoS₂-Au and Gr-MoS₂-Gr are shown in **Figure 4**.

For the Au-MoS₂-Gr heterostructure, we measured 44 devices in total and a typical output characteristic is shown in **Figure 3a**. We can see an obvious current rectification, allowing current to flow through only if the device is positively biased. It can be seen that the heterostructure functions as a diode connected with a resistor, as shown in the inset image of **Figure 3a**. To explain this rectification, we introduce Schottky barriers formed between Au-MoS₂ and Gr-MoS₂ interface. A Schottky barrier is formed between a metal-semiconductor interface. A Schottky barrier inhibits the flow of electrons (holes), allowing limited charge injection through tunneling and thermionic emissions. We can estimate the theoretical height of Schottky barrier using Schottky-Mott rule:

$$\Phi_{Schottky\ Barrier} = \Phi_{Metal} - \chi_{TMD}$$

in which Φ_{Metal} is the work function of metal (and graphene), χ_{TMD} is the electron affinity of semiconductor. Thus the height of Au-MoS₂ barrier is estimated to be $\Phi_{Au-MoS_2} = \Phi_{Au} - \chi_{MoS_2} = 5.1 - 4.0 = 1.1eV$.⁴⁰ The height of Gr-MoS₂ barrier is estimated to be $\Phi_{Gr-MoS_2} = \Phi_{Gr} - \chi_{MoS_2} = 4.6 - 4.0 = 0.6eV$. This Schottky barrier difference is the reason why rectification was observed in Au-MoS₂-Gr heterostructure: it's easier for electrons to tunnel from graphene to MoS₂ as the barrier is lower, giving rise to the measured current when positively biased. When negatively biased, electrons need to flow through a higher Au-MoS₂ barrier, resulting a much smaller measured current. Though we can roughly estimate the theoretical Schottky barrier

heights under static conditions, the effective barrier height may change under certain conditions such as external gating and laser exposure.

In **Figure 3a**, the forward voltage of the rectification is depicted by a tangent line of the linear part of the output curve, which is 1.1V in this case. The value of forward voltage is an important feature of diodes and is associated with the height difference of Schottky barriers in this structure. To better demonstrate the overall characteristics of the 44 devices, a statistic is shown in **Figure 3b**. The X axis is simply device numbers and the Y-axis is the dark current under different bias: $V_{ds} = 2V$ and $V_{ds} = -2V$, namely on-current and off-current. The current (y-axis) is shown in logarithmic scale in order to make the data comparable, and the negative sign of current is omitted. The current plotted in the y-axis is calibrated by the area of the efficient region. For example, if a MoS₂ domain only covers half of the channel (the active region is only $1\mu m \times 0.5 \times 20\mu m$), then the current is doubled. In brief, for each device, the two dotted points mean the absolute value of on-current and off-current when source-drain bias is +2V and -2V respectively. And the length of the line connecting two points stands for the rectification ratio, defined as on-current/off-current. We can see from the statistics that the overall off-current vary from 10^{-11} A to 10^{-9} A while the on-current has a larger variance, varying from 10^{-9} A to 10^{-5} A. The general rectification ratio about ~100 can be achieved and some devices perform pretty well, yielding a rectification ratio over 10^4 . The best one has a rectification ratio of 1.4×10^6 but it's not representative as the off-current of it is 10^{-12} A which is lower than the measurements limit (10^{-11} A). Though the performance of the devices varies a little bit, the pattern is quite clear. The distribution of the dark currents and forward voltages might result from the different doping levels of MoS₂ and graphene, so that the Schottky barrier heights are different.

External gating and laser illumination are common techniques to modulate properties of 2D materials, which were found have a substantial impact on the rectifying behavior of the device. **Figure 3c** shows the gate-dependence of rectification. The external voltage could increase both on-current and off-current. Under external gate voltage of $V_g = 10V, 20V, 30V$ and $40V$, the on-current increases by -3%, 32%, 64% and 153% compared to on-current without gating. The off-current increases by 28%, 40%, 92%, 67% in the meanwhile. The rectification ratio under various gate voltages remains around 10^4 , shown in **Figure 3e**. **Figure 3d** shows photocurrent of the device versus applied irradiation power intensity. A focused laser beam (nm) with various illumination power is used for optoelectronic measurements. The spot size of the beam is estimated to be $\sim 150 \mu m^2$. The photocurrent is defined as $I_{photo} = I_{illuminated} - I_{dark}$, which was extracted from I_{ds} - V_{ds} plots of the device under dark and illuminated conditions. The laser power dependence of rectification of the heterostructure was also observed. Laser irradiation could increase both on-current and off-current by several orders, the rectification ratio quickly decrease from 10^4 to about 40 at laser irradiation power of $2.53 \times 10^3 \text{ mW/cm}^2$, as shown in **Figure 3f**. This decrease of rectification ratio is primarily because the off-current is significantly increased under laser irradiation, indicating a reduced Au-MoS₂ Schottky barrier height, which is discussed later in **Figure 5c**. These results indicate that the modulation of the performance by external gating and laser irradiation are of different mechanisms. To study how Schottky barriers are influenced by them, we turn to Au-MoS₂-Au and Gr-MoS₂-Gr devices. Each of them can be seen as a Metal-Semiconductor-Metal (MSM) transistor, which consists of two back-to-back Schottky contacts.

Figure 4. Electronic and optoelectronic characteristics of the 2 symmetrical structures: Au-MoS₂-Au and Gr-MoS₂-Gr. (a) Gate-voltage dependence of the output characteristics of Au-MoS₂-Au structure. (b) Gate-voltage dependence of the output characteristics of the Gr-MoS₂-Gr structure. (c) Laser-power dependence of the output characteristics of Au-MoS₂-Au structure. (d) Laser-power dependence of the output characteristics of the Gr-MoS₂-Gr structure. (e) I_{ds} - V_g plot of Au-MoS₂-Au and Gr-MoS₂-Gr

heterostructure under drain-source bias = 1 V, showing the N-type nature of CVD-synthesized MoS₂ crystal.

(f) Photoresponsivity versus V_{ds} of the two types of devices, under illumination power density of 6.00×10^4 mW/cm².

The electronic and optoelectronic properties of Au-MoS₂-Au and Gr-MoS₂-Gr heterostructures are displayed in **Figure 4**. **Figure 4a** and **Figure 4b** show the dark current of Au-MoS₂-Au and Gr-MoS₂-Gr devices, under various gate voltages. The ranges are different so that MoS₂ with graphene electrodes doesn't break down under high voltage. The two devices both exhibited a non-linear I-V curve, even under high gate voltage. This shows that both MoS₂-Gr and MoS₂-Au interface are non-ideal contact, also known as the Schottky contact. The Schottky barrier contributes to the majority of the resistance and gives rise to the non-linearity, resulting in a much better channel conductivity of MoS₂ with graphene electrodes due to a lower Schottky Barrier height.

Figure 4c and **Figure 4d** show the photocurrent of Au-MoS₂-Au and Gr-MoS₂-Gr devices under various laser power ($\lambda=532$ nm). The output characteristics of Au-MoS₂-Au are still non-linear upon illumination. However, the output characteristics of Gr-MoS₂-Gr became near linear under illumination, suggesting a near Ohmic contact between Gr electrodes and MoS₂ domains under irradiation. To better describe the optoelectrical behavior of both types of devices, we introduce photoresponsivity (R), a measure of a device's electrical response to incident light, defined as $R = \frac{I_{photo}}{P_{light}}$, in which I_{photo} is the generated photocurrent and P_{light} the incident light power on the photosensors. **Figure 4f** shows the photoresponsivity of the two types of devices under an incident light power of 6.00×10^4 mW/cm². The photodetector with graphene electrodes shows higher photoresponsivity under ambient conditions, reaching 15 AW^{-1} at a bias of +1 V.

We can characterize the two devices as photodetectors using photoconductive gain. External photoconductive gain (G_{ext}) is the number of photo-excited charge carriers that are collected at the electrodes for each unit of incident photons on the photoconductor. External photoconductive gain is related to photoresponsivity through the following formula:

$R = G_{\text{ext}} \cdot e/h\nu$, where G_{ext} is the external photogain, e the elementary charge unit, h the Planck's constant and ν the incident photon frequency. As not all photons are absorbed by the MoS₂ layer, we can derive the internal photoconductive gain (G_{int}) using $G_{\text{int}} = G_{\text{ext}}/QE$, where QE is the quantum efficiency, equals to light absorbance for photoconductors. Assuming the light absorption rate and transmittance rate of MoS₂ under 532nm light (2.33 eV) are 10% and 90%,⁴¹ we are able to calculate the internal photoconductive gain for both types of devices. At a bias of $V_{\text{ds}} = 1\text{V}$, the internal photoconductive gain of MoS₂ with metal electrodes is 9 and MoS₂ with graphene electrodes is 353.

Specific detectivity (D^*) is also an important measure for photodetectors, which also considers the geometry, bandwidth and noise of the device. It's calculated as $D^* = \frac{R \times (Af)^{1/2}}{i_n}$, where A is the effective area of the detector, f is the electrical bandwidth, and i_n the noise current. For a simple estimation, we assume that the dark current is dominated by shot noise and is independent to frequency. Then D can be expressed as: $D^* = RA^{1/2}/(2eI_{\text{dark}})^{1/2}$, where R is the photoresponsivity of the device and I_{dark} is the dark current. The estimated detectivity of MoS₂ with Au electrodes is 8.8×10^{11} Jones (Jones = $\text{cm Hz}^{1/2} \text{W}^{-1}$) and the detectivity of MoS₂ with graphene electrodes is 1.2×10^{10} Jones, which is lower than that of Au-MoS₂-Au, due to a much higher dark current.

Figure 4e shows the field effect of the two types of MSM transistors. Both of the plots shows the N-type nature of CVD-grown MoS₂ domains, with a threshold voltage (V_{th}) of $\sim 10V$. Though the threshold voltage is supposed to be related to the Schottky barrier heights, the existence of trapped states will move the theoretical threshold voltage (V_{th}). The estimated mobility of both types of devices can be extracted from **Figure 4e**, using $\mu = \frac{dI_{ds}}{dV_g} \cdot \frac{L}{w} \cdot \frac{1}{V_{sd}} \cdot \frac{1}{C_{ox}}$, where L and w are the channel's length and width respectively, and C_{ox} is the oxide capacitance per unit area calculated by $C_{ox} = \frac{\epsilon_0 \epsilon_r}{d}$, in which ϵ_0 is the absolute permittivity, ϵ_r is the dielectric constant of SiO₂ and d is the thickness of the SiO₂ layer. The calculated mobility of MoS₂ with Au electrodes and Gr electrodes are 0.054 cm² V⁻¹ s⁻¹ and 4.21 cm² V⁻¹ s⁻¹ respectively.

In **Figure 4** we can see that laser irradiation and external gating could substantially impact the performance of MoS₂ by modulating the corresponding Schottky barrier heights between MoS₂ and metal (graphene). Though we have estimated the barrier heights under static conditions, it's difficult to estimate the change of barriers heights under external modulation. So we employed a Schottky barrier fitting method developed in our previous study.³⁹ Using a symmetrical structure, for example, Au-MoS₂-Au and Gr-MoS₂-Gr, we can simplify the MSM transistor into a circuit with two back-to-back Schottky diodes and a resistor. After fitting the I-V curves under the different gates and laser intensity (**Figure 4 a-d**) using a modified thermionic emission equation (supporting information), we are able to extract the Schottky barrier heights under certain conditions. The results are shown in **Figure 5**.

Figure 5. Mechanism of the tunable behavior explained by Schottky barrier change. (a). Band Schematic of a lateral Au-MoS₂-graphene heterostructure. (b) Calculated effective Schottky barrier height change of MoS₂-Au and MoS₂-Gr interface under various external gate voltages. (c) Calculated effective Schottky barrier height change of MoS₂-Au and MoS₂-Gr interface under various irradiation powers.

The gate dependence of Schottky barrier heights is shown in **Figure 5b**. Both Au-MoS₂ and Gr-MoS₂ barrier heights decrease as we increase back gate voltage. This is expected because it has been demonstrated in some prior results that gate voltage raises up graphene's Fermi level as well as moved down the conduction band of MoS₂.^{30,39} This is due to the nature of 2D materials: The limited density of states of 2D materials makes them very sensitive to the gate voltage. The simultaneous change of Au-MoS₂ and MoS₂-Gr barrier heights could explain the relative stable rectification ratio under gate voltage.

The laser density dependence of Schottky barrier heights is shown in **Figure 5c**. The impact of laser illumination on Au-MoS₂ and MoS₂-Gr barriers are of different degrees. Laser irradiation could quickly decrease the barrier height to 0.2 eV, and the heights difference quickly narrowed

down. This explains the quick drop of the rectification ratio of Au-MoS₂-Gr heterostructure under laser irradiation. The modification of Au-MoS₂ barriers under laser irradiation can be explained by photogating effect, which has been observed in the previous study.³⁰ At the incident of light, the electron-hole pairs can be generated. While electrons could migrate and contribute to photocurrent, holes could only reside in MoS₂ domains, due to the existence of trap states between MoS₂ and Au electrodes. The accumulated holes act as active gating to MoS₂ so that the barrier heights of Au-MoS₂ decreased quickly.

But for the graphene-MoS₂ barrier, the contact between these two 2D materials is good without a high density of trapped states. The decrease of barrier height results from the migration of photogenerated electrons. Those electrons traveled to graphene ribbons and reduced the work function of graphene (increased Fermi level), resulting in a decreased Schottky barrier height.

In summary, three types of heterostructure devices based on CVD-grown graphene and MoS₂ were fabricated. Their electronic and optoelectronic properties were measured. A significant rectification was observed in nearly all 44 Au-MoS₂-Gr devices, with a highest rectification ratio over 2×10^4 . The rectifying behaviour can be tuned by back-gate voltage and laser irradiation, but the impact on rectification ratio is different. Asymmetrical Schottky barriers of Au-MoS₂ and MoS₂-Gr interfaces are the reasons for the phenomenon. Schottky barriers of the two interfaces were estimated using output characteristics of Au-MoS₂-Au and Gr-MoS₂-Gr field effect transistors. The difference between Au-MoS₂ and MoS₂-Gr barrier heights quickly narrows down under laser irradiation, which explains the quick drop of rectification ratio. This study increases our understanding of 2D heterostructures and can be useful for future applications such as photosensors and gate-logics.

Experimental Methods

CVD Synthesis of Graphene film and MoS₂ domains. Monolayer graphene was synthesized using our previously reported method. A piece of copper foil is used as a catalyst and substrate for the deposition. The growth was conducted with a flow of 500 sccm Argon, 100 sccm Hydrogen (25% Hydrogen, 75% Argon), and 10 sccm Methane (1% Methane, 75% Argon) for 60 mins at 1060 °C. After the growth, the furnace was moved away to facilitate fast cooling for better graphene quality.

Monolayer MoS₂ domains were synthesized on a 300 nm SiO₂/Si substrate using molybdenum trioxide (MoO₃) and sulfur (S, >= 99.5%; Sigma-Aldrich) powders under atmospheric pressure. The two precursors were placed in a double-walled quartz tube at different positions. Sulfur and MoO₃ were then heated and vaporized by two independent furnaces at 180 and 300 °C respectively. The synthesis took 30 min after which the furnaces were cooled down.

Transfer of CVD-Grown Graphene and MoS₂. The as-grown graphene and MoS₂ samples were spin-coated with a poly(methyl methacrylate) (PMMA) scaffold (8 wt% in anisole, 495k molecular weight) at 4500 rpm for 60s and baked at 180°C for 90s. The substrate of graphene and MoS₂ were removed using a different solution. PMMA/graphene/copper sample was put in ammonium persulfate solution (0.2 mol/L) for 3 hours to detach the copper substrate.

PMMA/MoS₂/SiO₂/Si sample was put in KOH solution (1 mol/L) for 2 hours to dissolve SiO₂ and remove the Si substrate. Then the floating PMMA/graphene and PMMA/MoS₂ films were carefully scooped up with a glass slide and transferred 3 times into deionized water to clean the film. After that, the films were transferred onto SiO₂/Si chip and left in ambient environment overnight. Then the samples were baked at 150°C for 15 min. PMMA film was dissolved in hot acetone at 45°C for 3 hours, leaving 2D materials onto the chip.

Device Fabrication. The three structures were made using similar methods involving bond pads deposition, graphene etching, and 2D materials transfer. For all three types of devices, a bilayer PMMA (A8 495k, A8 950k) resist were spin-coated onto SiO₂(300nm)/Si chips. Then the resist is patterned using a JEOL 5500 FS EBL system. Bond pads of Cr(10nm)/Au(80nm) were deposited using thermal evaporation. For Au-MoS₂-Au device, the MoS₂ film was transferred onto the chip directly, using the transfer method described above. For Au-MoS₂-Gr and Gr-MoS₂-Gr devices, graphene films were transferred onto the chips and patterned using EBL, but with negative resist ma-N 2403. Oxygen plasma was employed to etch the graphene ribbons. In the end, MoS₂ was transferred on top of the chip.

Characterization of Materials. The device morphology is analyzed using a scanning electron microscope (Hitachi-4300) under an accelerating voltage of 3.0 kV. A Labram Aramis Raman Spectrometer was used to carry out Raman and PL spectroscopy for both graphene and MoS₂. The layer number and quality of the materials were examined.

Optoelectronic Characterization Devices. To characterize the electronic properties of the devices, highly conductive Si in the substrate was wired and connected to a socket as a back gate. A Keithley 2400 source meter connected with two tungsten tips was used for measuring output characteristics. The gate bias was applied by another Keithley 2400 source meter. A 532 nm diode-pumped solid-state laser (Thorlabs, DJ532-40) was integrated into a confocal microscope to generate a beam with a spot size of $\sim 150 \text{ } \mu\text{m}^2$ as a light source for optoelectronic properties.

Supporting Information

Supplementary information is available and contains, Optical microscopy images of heterostructure devices, time dependent photocurrent response of devices, and calculation of Schottky barrier heights.

Acknowledgements

JHW thanks the European Research Council for funding (725258), and the Royal Society.

Reference

- (1) Novoselov, K. S.; Fal'Ko, V. I.; Colombo, L.; Gellert, P. R.; Schwab, M. G.; Kim, K. A Roadmap for Graphene. *Nature* **2012**, *490*, 192–200.
- (2) Manzeli, S.; Ovchinnikov, D.; Pasquier, D.; Yazyev, O. V.; Kis, A. 2D Transition Metal Dichalcogenides. *Nat. Rev. Mater.* **2017**, *2*.
- (3) Ramakrishna Matte, H. S. S.; Gomathi, A.; Manna, A. K.; Late, D. J.; Datta, R.; Pati, S. K.; Rao, C. N. R. MoS₂ and WS₂ Analogues of Graphene. *Angew. Chemie - Int. Ed.* **2010**, *49*, 4059–4062.
- (4) Mak, K. F.; Lee, C.; Hone, J.; Shan, J.; Heinz, T. F. Atomically Thin MoS₂: A New Direct-Gap Semiconductor. *Phys. Rev. Lett.* **2010**, *105*, 2–5.
- (5) Radisavljevic, B.; Radenovic, A.; Brivio, J.; Giacometti, V.; Kis, A. Single-Layer MoS₂ transistors. *Nat. Nanotechnol.* **2011**, *6*, 147–150.
- (6) Ghatak, S.; Pal, A. N.; Ghosh, A. Nature of Electronic States in Atomically Thin MoS₂ Field-Effect Transistors. *ACS Nano* **2011**, *5*, 7707–7712.
- (7) Late, D. J.; Liu, B.; Matte, H. S. S. R.; Dravid, V. P.; Rao, C. N. R. Hysteresis in Single-Layer MoS₂ Field Effect Transistors. *ACS Nano* **2012**, *6*, 5635–5641.
- (8) Kong, D.; Wang, H.; Cha, J. J.; Pasta, M.; Koski, K. J.; Yao, J.; Cui, Y. Synthesis of MoS₂ and MoSe₂ films with Vertically Aligned Layers. *Nano Lett.* **2013**, *13*, 1341–1347.
- (9) Fang, H.; Chuang, S.; Chang, T. C.; Takei, K.; Takahashi, T.; Javey, A. High-Performance Single Layered WSe₂ p-FETs with Chemically Doped Contacts. *Nano Lett.* **2012**, *12*, 3788–3792.
- (10) Dean, C. R.; Young, A. F.; Meric, I.; Lee, C.; Wang, L.; Sorgenfrei, S.; Watanabe, K.;

- Taniguchi, T.; Kim, P.; Shepard, K. L.; *et al.* Boron Nitride Substrates for High-Quality Graphene Electronics. *Nat. Nanotechnol.* **2010**, *5*, 722–726.
- (11) Wang, Q. H.; Kalantar-Zadeh, K.; Kis, A.; Coleman, J. N.; Strano, M. S. Electronics and Optoelectronics of Two-Dimensional Transition Metal Dichalcogenides. *Nat. Nanotechnol.* **2012**, *7*, 699–712.
- (12) Jariwala, D.; Marks, T. J.; Hersam, M. C. Mixed-Dimensional van Der Waals Heterostructures. *Nat. Mater.* **2017**, *16*, 170–181
- (13) Radisavljevic, B.; Whitwick, M. B.; Kis, A. Integrated Circuits and Logic Operations Based on Single-Layer MoS₂. *ACS Nano* **2011**, *5*, 9934–9938.
- (14) Withers, F.; Del Pozo-Zamudio, O.; Mishchenko, A.; Rooney, A. P.; Gholinia, A.; Watanabe, K.; Taniguchi, T.; Haigh, S. J.; Geim, A. K.; Tartakovskii, A. I.; *et al.* Light-Emitting Diodes by Band-Structure Engineering in van Der Waals Heterostructures. *Nat. Mater.* **2015**, *14*, 301–306.
- (15) Withers, F.; Del Pozo-Zamudio, O.; Schwarz, S.; Dufferwiel, S.; Walker, P. M.; Godde, T.; Rooney, A. P.; Gholinia, A.; Woods, C. R.; Blake, P.; *et al.* WSe₂ Light-Emitting Tunneling Transistors with Enhanced Brightness at Room Temperature. *Nano Lett.* **2015**, *15*, 8223–8228.
- (16) Gong, Y.; Lin, J.; Wang, X.; Shi, G.; Lei, S.; Lin, Z.; Zou, X.; Ye, G.; Vajtai, R.; Yakobson, B. I.; *et al.* Vertical and In-Plane Heterostructures from WS₂ /MoS₂ Monolayers. *Nat. Mater.* **2014**, *13*, 1135–1142.
- (17) Cheng, R.; Li, D.; Zhou, H.; Wang, C.; Yin, A.; Jiang, S.; Liu, Y.; Chen, Y.; Huang, Y.; Duan, X. Electroluminescence and Photocurrent Generation from Atomically Sharp WSe₂/MoS₂ heterojunction p-n Diodes. *Nano Lett.* **2014**, *14*, 5590–5597.

- (18) Furchi, M. M.; Pospischil, A.; Libisch, F.; Burgdörfer, J.; Mueller, T. Photovoltaic Effect in an Electrically Tunable Van Der Waals Heterojunction. *Nano Lett.* **2014**, *14*, 4785–4791.
- (19) Huo, N.; Wei, Z.; Meng, X.; Kang, J.; Wu, F.; Li, S.-S.; Wei, S.-H.; Li, J. Interlayer Coupling and Optoelectronic Properties of Ultrathin Two-Dimensional Heterostructures Based on Graphene, MoS₂ and WS₂. *J. Mater. Chem. C* **2015**, *3*, 5467–5473.
- (20) Tian, H.; Tan, Z.; Wu, C.; Wang, X.; Mohammad, M. A.; Xie, D.; Yang, Y.; Wang, J.; Li, L. J.; Xu, J.; *et al.* Novel Field-Effect Schottky Barrier Transistors Based on Graphene-MoS₂ Heterojunctions. *Sci. Rep.* **2014**, *4*, 1–9.
- (21) Yu, L.; Lee, Y. H.; Ling, X.; Santos, E. J. G.; Shin, Y. C.; Lin, Y.; Dubey, M.; Kaxiras, E.; Kong, J.; Wang, H.; *et al.* Graphene/MoS₂ Hybrid Technology for Large-Scale Two-Dimensional Electronics. *Nano Lett.* **2014**, *14*, 3055–3063.
- (22) Sup Choi, M.; Lee, G. H.; Yu, Y. J.; Lee, D. Y.; Hwan Lee, S.; Kim, P.; Hone, J.; Yoo, W. J. Controlled Charge Trapping by Molybdenum Disulphide and Graphene in Ultrathin Heterostructured Memory Devices. *Nat. Commun.* **2013**, *4*, 1624–1627.
- (23) Roy, K.; Padmanabhan, M.; Goswami, S.; Sai, T. P.; Ramalingam, G.; Raghavan, S.; Ghosh, A. Graphene-MoS₂ Hybrid Structures for Multifunctional Photoresponsive Memory Devices. *Nat. Nanotechnol.* **2013**, *8*, 826–830.
- (24) Yu, W. J.; Liu, Y.; Zhou, H.; Yin, A.; Li, Z.; Huang, Y.; Duan, X. Highly Efficient Gate-Tunable Photocurrent Generation in Vertical Heterostructures of Layered Materials. *Nat. Nanotechnol.* **2013**, *8*, 952–958.
- (25) Georgiou, T.; Jalil, R.; Belle, B. D.; Britnell, L.; Gorbachev, R. V.; Morozov, S. V.;

- Kim, Y. J.; Gholinia, A.; Haigh, S. J.; Makarovsky, O.; *et al.* Vertical Field-Effect Transistor Based on Graphene-WS₂ Heterostructures for Flexible and Transparent Electronics. *Nat. Nanotechnol.* **2013**, *8*, 100–103.
- (26) Bertolazzi, S.; Krasnozhon, D.; Kis, A. Nonvolatile Memory Cells Based on MoS₂/Graphene Heterostructures. *ACS Nano* **2013**, *7*, 3246–3252.
- (27) Kim, K.; Larentis, S.; Fallahazad, B.; Lee, K.; Xue, J.; Dillen, D. C.; Corbet, C. M.; Tutuc, E. Band Alignment in WSe₂-Graphene Heterostructures. *ACS Nano* **2015**, *9*, 4527–4532.
- (28) Kwak, J. Y.; Hwang, J.; Calderon, B.; Alsalman, H.; Munoz, N.; Schutter, B.; Spencer, M. G. Electrical Characteristics of Multilayer MoS₂ FETs with MoS₂/Graphene Heterojunction Contacts. *Nano Lett.* **2014**, *14*, 4511–4516.
- (29) Lin, Y.-F.; Li, W.; Li, S.-L.; Xu, Y.; Aparecido-Ferreira, A.; Komatsu, K.; Sun, H.; Nakaharai, S.; Tsukagoshi, K. Barrier Inhomogeneities at Vertically Stacked Graphene-Based Heterostructures. *Nanoscale* **2014**, *6*, 795–799.
- (30) Tan, H.; Fan, Y.; Zhou, Y.; Chen, Q.; Xu, W.; Warner, J. H. Ultrathin 2D Photodetectors Utilizing Chemical Vapor Deposition Grown WS₂ with Graphene Electrodes. *ACS Nano* **2016**, *10*, 7866–7873.
- (31) Sze, S. M.; Ng, K. K. *Physics of Semiconductor Devices*; John Wiley & Sons: New York, **2006**.
- (32) Allain, A.; Kang, J.; Banerjee, K.; Kis, A. Electrical Contacts to Two-Dimensional Semiconductors. *Nat. Mater.* **2015**, *14*, 1195–1205.
- (33) Sheng, Y.; Rong, Y.; He, Z.; Fan, Y.; Warner, J. H. Uniformity of Large-Area Bilayer Graphene Grown by Chemical Vapor Deposition. *Nanotechnology* **2015**, *26*.

- (34) Wang, S.; Rong, Y.; Fan, Y.; Pacios, M.; Bhaskaran, H.; He, K.; Warner, J. H. Shape Evolution of Monolayer MoS₂ Crystals Grown by Chemical Vapor Deposition. *Chem. Mater.* **2014**, *26*, 6371–6379.
- (35) Fan, Y.; He, K.; Tan, H.; Speller, S.; Warner, J. H. Crack-Free Growth and Transfer of Continuous Monolayer Graphene Grown on Melted Copper. *Chem. Mater.* **2014**, *26*, 4984–4991.
- (36) Malard, L. M.; Pimenta, M. A.; Dresselhaus, G.; Dresselhaus, M. S. Raman Spectroscopy in Graphene. *Phys. Rep.* **2009**, *473*, 51–87.
- (37) Najmaei, S.; Liu, Z.; Zhou, W.; Zou, X.; Shi, G.; Lei, S.; Yakobson, B. I.; Idrobo, J. C.; Ajayan, P. M.; Lou, J. Vapour Phase Growth and Grain Boundary Structure of Molybdenum Disulphide Atomic Layers. *Nat. Mater.* **2013**, *12*, 754–759.
- (38) Bhanu, U.; Islam, M. R.; Tetard, L.; Khondaker, S. I. Photoluminescence Quenching in Gold - MoS₂ Hybrid Nanoflakes. *Sci. Rep.* **2015**, *4*, 5575.
- (39) Tan, H.; Fan, Y.; Rong, Y.; Porter, B.; Lau, C. S.; Zhou, Y.; He, Z.; Wang, S.; Bhaskaran, H.; Warner, J. H. Doping Graphene Transistors Using Vertical Stacked Monolayer WS₂ Heterostructures Grown by Chemical Vapor Deposition. *ACS Appl. Mater. Interfaces* **2016**, *8*, 1644–1652.
- (40) Yu, Y.-J.; Zhao, Y.; Ryu, S.; Brus, L. E.; Kim, K. S.; Kim, P. Tuning the Graphene Work Function by Electric Field Effect. *Nano Lett.* **2009**, *9*, 3430–3434.
- (41) Bernardi, M.; Palummo, M.; Grossman, J. C. Extraordinary Sunlight Absorption and One Nanometer Thick Photovoltaics Using Two-Dimensional Monolayer Materials. *Nano Lett.* **2013**, *13*, 3664–3670.
- (42) Fan, Y.; Zhou Y.; Wang, X.; Tan, H.; Rong, Y.; Warner, J.H. Photoinduced Schottky

Barrier Lowering in 2D Monolayer WS₂ Photodetectors. *Adv. Opt. Mater.* **2016**, Early

View, DOI: 10.1002/adom.201600221

TOC graphic